

REPORT DOCUMENTATION PAGE

AFRL-SR-AR-TR-03-

0857

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, gathering existing data needed, and completing and reviewing this collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, (704-018-4302). Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not have a unique OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.

1. REPORT DATE (DD-MM-YYYY) April 28, 2003		2. REPORT TYPE Final		3. DATES COVERED (From - To) 12/15/99 - 11/29/02	
4. TITLE AND SUBTITLE Fundamental Studies for High Temperature Superconductor Conductor Technology				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER F49620-00-1-0091	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S) David C Larbalestier				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Applied Superconductivity Center University of Wisconsin - Madison				8. PERFORMING ORGANIZATION REPORT NUMBER	
				1500 Engineering Drive Room 909 ERB Madison WI 53706-1609	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) AFOSR/NE 801 N. Randolph St. Room 732 Arlington VA 22203-1977 (Attn: Dr Harold Weinstock)				10. SPONSOR/MONITOR'S ACRONYM(S) AFOSR	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION STATEMENT A Approved for Public Release Distribution Unlimited				AIR FORCE OFFICE OF SCIENTIFIC RESEARCH (AFOSR) NOTICE OF TRANSMITTAL DTIC. THIS TECHNICAL REPORT HAS BEEN REVIEWED AND IS APPROVED FOR PUBLIC RELEASE LAW AFR 190-12. DISTRIBUTION IS UNLIMITED.	
13. SUPPLEMENTARY NOTES					
14. ABSTRACT There is strong Air Force interest in compact, airborne, high-power generators and klystron/gyrotron/magnetron magnets for radar applications. Both applications need superconducting magnets but, to be practical, superconducting magnets must be made with high temperature superconductors (HTS) capable of being refrigerated by robust cryocoolers at temperatures near liquid nitrogen (77K). The pacing element for all such applications is the conductor from which such magnets can be made. The material of choice for this conductor is YBa ₂ Cu ₃ O _{7-x} , made in the form of a multilayer tape as a Coated Conductor. This report proposal describes research carried out in support of this effort from 1999-2002. Our global thrusts were to understand the ultimate critical current potential of YBCO in coated conductor form. To this end we performed the following work under this contract: 1. Studies of current limiting mechanisms in Coated Conductor samples, 2. Studies of the microstructure of buffer and YBCO layers of Coated Conductors, 3. Analysis of the influence of obstructions to current flow and local dissipation, and 4. Facility development in support of our research program..					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON David C Larbalestier
a. REPORT	b. ABSTRACT	c. THIS PAGE			19b. TELEPHONE NUMBER (include area code) (608) 263 2194

BEST AVAILABLE COPY

Standard Form 298 (Rev. 8-98)
Prescribed by ANSI Std. Z39.18

20031006 082

Fundamental Studies for High Temperature Superconductor Conductor Technology

AFOSR Grant F49620-00-1-009f

Final Report

December 15, 1999 – November 29, 2002

PI: David C Larbalestier
University of Wisconsin-Madison
Applied Superconductivity Center
1500 Engineering Drive, 909 ERB
Madison, WI 53706
(608) 263 2194 phone
(608) 263 1087 fax
larbalestier@engr.wisc.edu

OBJECTIVES

Developing high critical current density (J_c) in conductors is the most essential step to developing attractive power technologies from high temperature superconductors (HTS). HTS materials possess attractively high J_c values over a large domain of temperature and field but real conductors contain many defects that limit the transport current density below their very high local values. Our goal is to understand the current limiting mechanisms of actual and prototype coated conductor (CC) forms. Two generations of conductor form are discussed today, a first generation based on $(\text{Bi,Pb})_2\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_x$, which is available now in kilometer lengths, and a second generation conductor based on biaxially aligned $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$, which has received a proof of principle in short lengths. During 2002 came the first continuously processed lengths from industry with properties exceeding 100 A over 1 meter. This success is a result of intense effort on scaling up YBCO coated conductors in the national labs and in industry, with strong support from university programs such as this one. The central focus of our work has been to understand the way in which the connectivity determines the J_c of YBCO conductor forms. Our major effort was to use coordinated studies of the voltage-current characteristics, magneto optical imaging, microstructural analysis and theoretical study of the percolation of current around obstacles to understand the critical current density. This integrated view was then used to raise the properties of the whole conductor.

Collaboration is an essential component of our work. Some samples we make ourselves but a vital part of our work was that we received samples from many leading groups. Our work was guided by our strong linkages with the leading groups in the field at American Superconductor Corp. (ASC), ORNL, LANL, and the AFRL. This grant also provided the seed for the MURI on Fundamental Science of Coated Conductors, which started in July 2001.

DISTRIBUTION STATEMENT A
Approved for Public Release
Distribution Unlimited

SUMMARY OF WORK COMPLETED

The global thrusts of the work were to understand the ultimate critical current potential of YBCO in coated conductor form. To this end we have performed the following work under this contract:

1. Studies of current limiting mechanisms in Coated Conductor samples.
2. Studies of the microstructure of buffer and YBCO layers of Coated Conductors.
3. Analysis of the influence of obstructions to current flow and local dissipation.
4. Facility development.

1. Current limiting mechanisms

(CLM) in coated conductors have been studied primarily by Magneto optical (MO) imaging coupled with Electron Backscatter Kikuchi Pattern (EBKP) analysis and by "micro- J_c " transport measurements. This work was collaborative, being performed on AMSC, AFRL and ORNL samples. The added capability of nano-volt transport measurements to our MO facility allowed us to image RABiTS-type CC samples from both AMSC and ORNL under an applied transport current. We were able to directly show that current percolates in these conductors from well before the onset of measurable dissipation (current much less than I_c) to well after (current greater than I_c). We observed that dissipation is often quite localized, with much of the sample carrying current well below the local J_c , even at applied transport currents well above the macroscopic J_c of the entire sample. This directly demonstrated untapped potential in these conductors. The results of the MO studies led us to further examine the local J_c in these conductors via "micro- J_c " transport measurements, where links no larger than $10 \times 30 \mu\text{m}$ were placed across single GBs and within single substrate grains in RABiTS-type CCs. In one sample an intra-grain J_c of 5.1 MA/cm^2 was measured in a sample with a full width J_c of only 1.2 MA/cm^2 , further demonstrating that current must be percolating through these conductors. Most intra-grain J_c values measured exceeded full-width J_c values. Electron Backscatter Kikuchi Pattern (EBKP) analysis was used to measure the GB angles of the inter-grain links, and the $J_c(\theta)$ dependence observed in RABiTS-type CCs matched well with bi-crystal studies.

2. Studies of the microstructure of buffer and YBCO overlayers:

We studied the relative orientations of the underlying Ni substrate, the buffer layers, and the YBCO in a RABiTS-type CC. XRD studies of CC suggested a sharpening of the c-axis alignment in the YBCO relative to the substrate, but were not convincing. Using Electron Backscatter Kikuchi Pattern (EBKP) analysis and ion milling to remove the layers of the CC, we were able to track the changes in individual GB angles from the substrate through the buffer layers and into the YBCO. We found that there was in fact a sharpening of the c-axis alignment of the YBCO, and that this generally led to reduced GB angles in the YBCO relative to the substrate. This is a positive result, with GB angles improving by more than 1 degree on average, though some GB angles increased as well.

3. Analysis of the influence of obstructions to current flow and their influence on local dissipation:

We performed extensive calculations of current flow and dissipation around planar obstacles in coated conductors using the newly developed hodograph method, which enabled us for the first time to obtain exact solutions of the Maxwell equations using the highly nonlinear E-J characteristics of superconductors. The results show that this non-linearity of the E(J) characteristics causes significant spread of the electric field and dissipation field on scales much greater than the defect size. These features cause even sparse arrays of small obstacles to act as important current-blocking effects, significantly reducing the effective current-carrying cross-section of coated conductors. Extended hot spots of strong electric field and dissipation near planar defects can trigger thermal instabilities, which limit the current-carrying capability of coated conductors. We developed analytical formulas for the power dissipation near defects and the global average of the critical current density (i.e. that which is measured), taking into account localized electric field hot spots in a distributed array of planar obstacles. We used this to calculate the thermal runaway current, which causes local thermal instability near defects. The obtained results are in agreement with recent laser scanning microscopy and magneto-optical studies, which allow direct visualization of electric field and current distributions in coated conductors.

4. Facility Development:

- A. In early 2000 we added the ability to perform *in-situ* transport measurements with a voltage resolution of < 10 nV to our MO facility. This ability allows us to directly image the self-field of a sample and hence the percolative behavior of current flow in CCs.
- B. In late 2002, we purchased a new cryostat for MO imaging under an applied transport current, which when ready, will allow us to apply much higher currents and therefore study samples with larger links or higher J_c values.
- C. In the middle of 2002, we added pulsed-current transport measure capability to our 14/16 T Oxford Magnet System to meet the large I_c demands of newer CCs. Using a current pulse of only 50 ms and a voltage read of 10 ms, we are able to obtain a voltage of < 50 nV. The pulsed-current system is readily expandable to 80A or more.

Publications supported wholly or in apart by the grant.

2000 Publications

S. E. Babcock, D. M. Feldmann, D. C. Larbalestier, A. A. Polyanskii, J. L. Reeves, and C. Yang, "Connections Among Substrate Structure, YBCO Microstructure and Critical Current Density in RABIT-Type Coated Conductors," in proceedings of International Workshop on Superconductivity (ISTEC), Shimane Prefecture, Japan, June 19, 2000, pp. 177-180.

D. M. Feldmann, J. L. Reeves, A. A. Polyanskii, G. Kozlowski, R. R. Biggers, R. M. Nekkanti, I. Maartense, M. Tomsic, P. Barnes, C. E. Oberly, T. L. Peterson, S. E. Babcock, and D. C. Larbalestier, "Influence of Nickel Substrate Grain Structure on YBa₂Cu₃O_{7-x} Supercurrent Connectivity in Deformation-Textured Coated Conductors," *Applied Physics Letters*, 77(18): 2906-2908, 2000.

A. Gurevich and M. Friesen, "Nonlinear Transport Current Flow in Superconductors with Planar Obstacles," *Physical Review B*, 62(6): 4004-4025, 2000.

A. Ichinose, C. Yang, G. Daniels, S. Liao, D. C. Larbalestier, S. E. Babcock, A. Kikuchi, K. Tachikawa, and S. Akita, "Studies of the Improvement in Microstructure of Y_2O_3 Buffer Layers and its Effect on $YBa_2Cu_3O_{7-x}$ Film Growth," *Superconductor Science & Technology*, 13, 1023-1028, 2000.

C. Yang, A. Pashitski, A. Polyanskii, D. C. Larbalestier, S. E. Babcock, A. Goyal, F. A. List, C. Park, M. Paranthaman, D. P. Norton, D. F. Lee, and D. M. Kroeger, "Microstructural Homogeneity and Electromagnetic Connectivity of $YBa_2Cu_3O_{7.5}$ Grown on Rolling-Assisted Biaxially Textured Coated Conductor Substrates," *Physica C*, 329: 114-120, 2000.

G. Daniels, A. Gurevich and D.C. Larbalestier, "Improved Strong Magnetic Field Performance of Low Angle Grain Boundaries of Calcium and Oxygen Overdoped $YBa_2Cu_3O_x$ ", *Applied Physics Letters*, 77, 3251-3253 (2000).

2001 Publications

R. N. Bhattacharya, M. Feldmann, D. Larbalestier, and R. D. Blaugher, "Electrodeposition Process for the Preparation of Superconducting Thallium Oxide Films," *IEEE Transactions on Applied Superconductivity*, 11(1): 3102-3105, 2001.

J. W. Ekin, S. L. Bray, N. Cheggour, C. C. Clickner, S. R. Foltyn, P. N. Arendt, A. A. Polyanskii, D. C. Larbalestier, and C. N. McCowan, "Transverse Stress and Fatigue Effects in Y-Ba-Cu-O Coated IBAD Tapes," *IEEE Transactions on Applied Superconductivity*, 11(1): 3389-3392, 2001.

C. B. Eom, M. K. Lee, J. H. Choi, L. Belenky, X. Song, L. D. Cooley, M. T. Naus, S. Patnaik, J. Jiang, M. Rikel, A. Polyanskii, A. Gurevich, X. Y. Cai, S. D. Bu, and et al, "High Critical Current Density and Enhanced Irreversibility Field in Superconducting MgB_2 Thin Films," *Nature*, 411: 558-560, 2001.

D. M. Feldmann, J. L. Reeves, A. A. Polyanskii, A. Goyal, R. Feenstra, D. F. Lee, M. Paranthaman, D. M. Kroeger, D. K. Christen, S. E. Babcock, and D. C. Larbalestier, "Magneto-Optical Imaging of Transport Currents in $YBa_2Cu_3O_{7.5}$ on RABiTS," *IEEE Transactions on Applied Superconductivity*, 11(1): 3772-3775, 2001.

D. M. Feldmann, D. C. Larbalestier, D. T. Verebelyi, W. Zhang, Q. Li, G. N. Riley, R. Feenstra, A. Goyal, D. F. Lee, M. Paranthaman, D. M. Kroeger, and D. K. Christen, "Inter- and Intragrain Transport Measurements in $YBa_2Cu_3O_{7.5}$ Deformation Textured Coated Conductors," *Applied Physics Letters*, 79(24): 3998-4000, 2001.

D. M. Feldmann, "Current Flow in $YBa_2Cu_3O_{7.5}$ Deformation Textured Coated Conductors," Ph.D. Thesis, Physics Department, University of Wisconsin-Madison, September, 2001.

Mark Friesen and Alex Gurevich "Nonlinear current flow in superconductors with restricted geometries". *Physical Review B* 63, 064521 1-26 (2001).

A. Gurevich, "Thermal Instability Near Planar Defects in Superconductors," *Applied Physics Letters*, 78(13): 1891-1893, 2001.

D. Larbalestier, A. Gurevich, D. M. Feldmann, and A. Polyanskii, "High-Tc Superconducting Materials for Electric Power Applications," *Nature*, 414: 368-377, 2001.

D. C. Larbalestier, L. D. Cooley, M. O. Rikel, A. A. Polyanskii, J. Jiang, S. Patnaik, X. Y. Cai, D. M. Feldmann, A. Gurevich, A. A. Squitieri, M. T. Naus, C. B. Eom, E. E. Hellstrom, R. J. Cava, and et al, "Strongly Linked Current Flow in Polycrystalline Forms of the Superconductor MgB_2 ," *Nature*, 410: 186-189, 2001.

D. C. Larbalestier, "Critical Currents: Just How Critical Are They?," *IEEE Transactions on Applied Superconductivity*, 11(1): 2685, 2001.

S. Patnaik, L. D. Cooley, A. Gurevich, A. A. Polyanskii, J. Jiang, X. Y. Cai, A. A. Squitieri, M. T. Naus, M. K. Lee, J. H. Choi, L. Belenky, S. D. Bu, J. Letteri, X. Song, and et al, "Electronic Anisotropy, Magnetic Field-Temperature Phase Diagram and their Dependence on Resistivity in c-Axis Oriented MgB_2 Thin Films," *Superconductor Science & Technology*, 14(6): 315-319, 2001.

J. L. Reeves, D. M. Feldmann, C. Yang, and D. C. Larbalestier, "Current Barriers in Y-Ba-Cu-O Coated Conductors," *IEEE Transactions on Applied Superconductivity*, 11(1): 3863-3867, 2001.

J. Reeves, "Microstructural Investigation of Current Barriers in High Temperature Superconducting Tapes and Coated Conductors," Ph.D. Thesis, Materials Science Program, University of Wisconsin-Madison, 1 June, 2001.

2002 Publications

A. Gurevich, M. S. Rzchowski, G. Daniels, S. Patnaik, B. M. Hinaus, F. Carillo, F. Tafuri, and D. C. Larbalestier, "Flux Flow of Abrikosov-Josephson Vortices Along Grain Boundaries in High-Temperature Superconductors," *Physical Review Letters*, 88(9): 097001/1-097001/4, 2002.

A. Gurevich. "Nonlinear dynamics of vortices in easy flow channels along grain boundaries in superconductors", *Physical Review B* 65, 214531-16 (2002).

A. A. Polyanskii, D. M. Feldmann, and D. C. Larbalestier, "Magneto-Optical Characterization Techniques," accepted for publication in D. Cardwell and D. Ginley, eds., "Handbook of Superconducting Materials," Institute of Physics Publishing, 2002.

C. Y. Yang, S. E. Babcock, A. Ichinose, A. Goyal, D. M. Kroeger, D. F. Lee, F. A. List, D. P. Norton, J. E. Mathis, M. Paranthaman, and C. Park, "Microstructure of Pulsed Laser Deposited

$\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ Films on Ytria-Stabilized Zirconia/ CeO_2 Buffered Biaxially Textured Ni Substrates," accepted for publication in Physica C, August, 2002.